

## DATA SHEET: EURO-HS CW617N

**FREE MACHINING** 



# EURO-HS CW617N



High workability alloy and reduced lead	The demand for alloys with reduced lead content, but with high machinability due to chip removal, has allowed the development of a high performance alloy. Inserted in the "Positive List" of the 4MS it is usable up to 10% of the surface of the domestic system of distribution of drinking water.
content.	

NAME OF ALLOY							
UNI EN: CW617N - CuZn40Pb2			<b>TM:</b> C37700	<b>DIN</b> : 2.0402	<b>BS:</b> CZ1	22 <b>GO</b>	<b>ST:</b> LS59-2
CHEMICAL COMPOSITION UNI EN 12164 ED.2016							
Cu	Pb*	Sn	Fe	Ni*	Si*	Zn	Other elements
min. 57.0 max. 59.0 %	1.6 2.2 %	≤0.3 %	≤0.3 %	≤0.1 %	≤0.03 %	difference	≤0.2 %

\*Limitation according 4MS. Elements not listed must be  $\leq 0.02$  %. Group of restriction of the surface in contact with drinking water: B,D.

#### **HEAT TREATMENTS**

STRESS RELIEVING	ANNEALING					
Enables the redistribution of tensions induced	by Re-crystallizes the alloy, reducing its hardness and					
mechanical processing of cold plastic deformat	ion, increasing its ductility.					
reducing the risk of stress corrosion cracking.	The temperature of the treatment varies from 450°C					
The treatment consists of heating the items to	to 550°C for an amount of time relative to the required					
200°C - 250°C for 2 hours and cooling within	the results. The high temperature can induce changes in					
furnace. The validation of the stress relieve	ving the surface appearance and in the tolerance of the					
treatment can be performed with the ISO 6957 te	est. finished part.					
MECHANICAL PROPERTIES UNI EN 12164 ED.2016						
Condition Diameter in mm Hardness H	B* Rm Rp <sub>0.2</sub> N/mm <sup>2</sup> Elongation %					

Condition	Diameter in mm		Hardness HB*		Rm	Rp <sub>0.2</sub> N/mm <sup>2</sup>		Elongation %
of material	from	to (included)	min.	max.	min.	min.	max.	min.
Μ	All		All		As a product			
R360	6	80	-	-	360	-	320	20
H090	6	80	90	125	-	-	-	-
R430	2	40	-	-	430	220	-	10
H110	2	40	110	160	-	-	-	-
R500	2	14	-	-	500	350	-	5
H135	2	14	135	-	-	-	-	-

\*the hardness value is determined in the mid-range The standard condition produced by Almag is R500 from Ø > 6 to Ø < 11 and R430 from Ø > 11 for Rm, or H110 for hardness. Any other conditions must be requested when ordering - subject to feasibility request.



### EURO-HS CW617N

High workability alloy and reduced lead content.

### ALMAG

<b>TECHNOLOGICAL PROPER</b>	RTIES	low excellent			
Structure	α+β	Machinability			
Density	8.4 kg/cm <sup>2</sup>	Weldability			
Electrical conductivity	27% IACS	Hot forming			
Coeff. of thermal expansion	20.7 10 <sup>-6</sup> /K	Cold forming			
Thermal conductivity*	120 W/(m K)	Corrosion resistance**	Not resistant		
Specific heat	380 J/(kg K)	*at room temperature **use care to ascertain compatibility with chemical substances			
Elasticity module	105 kN/mm <sup>2</sup>				
Melting point	880-895 °C				

#### DIMENSIONS, TOLERANCES, AND STRAIGHTNESS UNI EN 12164 ED.2016

#### ROUND section bar

ameter (mm)		TOLERANCES	
to included	Class A	Class B	Class C
10	0 - 0.06	0 - 0.036	0 - 0.025
18	0 - 0.07	0 - 0.043	
30	0 - 0.08	0 - 0.052	
50	0 - 0.16		
80	0 - 0.19		
	to included           10           18           30           50	to included         Class A           10         0 - 0.06           18         0 - 0.07           30         0 - 0.08           50         0 - 0.16	to included         Class A         Class B           10         0 - 0.06         0 - 0.036           18         0 - 0.07         0 - 0.043           30         0 - 0.08         0 - 0.052           50         0 - 0.16

The standard tolerance for the round bar is Class A. Any different tolerances must be agreed upon when ordering Semi-finished products can be supplied from Ø63 to Ø80 mm with Class A tolerances

Diam	neter m)	Length of bar (mm)	Tolerance (mm)	Diameter or Key (mm)		Diameter		Deviation from	m straightness in mm
2	30	3000 o 4000	+/- 50			Every 400 mm	Every m of length $L \ge 1$		
2				Round section bar					
30	50	3000 o 4000	+/- 100			Round Section	Sul		
50	80	3000	+/- 100	10	50	0.4	1.0 x L		

BAR FINISHING AND PACKAGING						
	neter Im)		nfer L mm		ip h L mm	30°
5	10	0.2	1.5	2	7	
10	20	0.2	2	3	10	
20	30	0.2	3	4	12	

Unless otherwise specified by the buyer, the shape of the ends of products larger than 30 mm is up to the supplier

Ends of round bars	finishing with chamfer and tip up to and including Ø40 mm finishing with chamfer and cut greater than Ø40 mm
Bar surface	pickled
Packaging	1000 kg bundle – 3/5 metal straps different bundle packagings and quantities are possible upon request
Identification	adhesive label on bundle strap
Stress relieving	the polygonal bar was subjected to stress relieving treatment



COMPANY WITH MANAGEMENT SYSTEM CERTIFIED BY DNV GL = ISO 9001 = = ISO 14001 = = OHSAS 18001 =





www.almag.it

 ALMAG S.p.A. AZIENDA LAVORAZIONI METALLURGICHE E AFFINI GNUTTI

 Single-member S.p.A.

 25030 Roncadelle (BS) - Via Vittorio Emanuele II n. 39 - Fully paid share capital € 2.000.000

 Tel. +39 030 2789511 - Fax +39 030 2789680 (admin.) - Fax +39 030 2789690 (sales)

 F.C./VAT and Brescia Chamber of Comm. Reg. No.03368970988-R.E.A. No.528368-Cert. email almagspa@legalmail.it

